



8018-C3 XLM

AWS E8018-C3 H4 (Ni1)

REPLACES: 060118

140-H, INDEX: 060515

DESCRIPTION:

With a notch toughness of 75 ft-lbs at -40°F, **McKay 8018-C3 XLM** is excellent for low temperature applications requiring tensile strengths of at least 80,000 psi and 1% nickel deposits. It provides exceptional puddle control with good wetting action and tie in. Plus, with its special formulated coating that reduces moisture pick-up, the McKay 8018-C3 XLM is also great in conditions of high heat and humidity. Note: Actual certs are supplied with every shipment (one per master carton or pallet) at no charge.

APPLICATIONS:

Used in shipbuilding, piping and gas storage tanks. Ideal for welding 1% Ni, low alloy, high-strength steels where tough welds at sub-zero temperatures are required.

FEATURES	BENEFITS
<ul style="list-style-type: none"> • Low hydrogen, less than 4 ml/100 g • Excellent arc characteristics • Low spatter level • Low moisture reabsorption • Quick and easy slag removal • Low smoke level 	<ul style="list-style-type: none"> • Resistant to hydrogen-induced cracking • Stable, easy to control arc • Improves weld bead appearance, higher deposition • Prevents starting porosity • Reduces clean-up time • Welder safety and comfort

TYPICAL WELD METAL PROPERTIES* (CHEM PAD):

WELD METAL ANALYSIS		AWS Spec
Carbon (C)	0.05	0.12 max
Manganese (Mn)	0.90	0.40 to 1.25
Phosphorus (P)	0.01	0.03 max
Sulphur (S)	0.01	0.03 max
Silicon (Si)	0.45	0.80 max
Chromium (Cr)	0.091	0.15 max
Vanadium (V)	0.008	0.05 max
Nickel (Ni)	0.95	0.80 to 1.10
Molybdenum (Mo)	0.16	0.35 max

TYPICAL MECHANICAL PROPERTIES*(AS WELDED):

		AWS Spec
Tensile Strength	87,000 psi (580 MPa)	80,000 psi, min
Yield Strength	73,200 psi (505 MPa)	68,000-80,000 psi, min
Elongation % in 2"	30%	24% min
Reduction of Area	71%	Not required

TYPICAL CHARPY V-NOTCH IMPACT VALUES*:

		AWS Spec
Avg. at -40°F (-40°C)	114 ft•lbf (102 J)	20 ft•lbf

CONFORMANCES AND APPROVALS:

- AWS Spec A5.5, Class E8018-C3 H4 • ASME SFA5.5, F-4, A-10, E8018-C3 H4 • ABS

*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and McKay expressly disclaims any liability incurred from any reliance thereon. Typical data are obtained when welded and tested in accordance with AWS A5.5 specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by McKay.



8018-C3 XLM

RECOMMENDED WELDING PROCEDURES:

- GENERAL:** DCEP (electrode positive, work negative) or AC
- ARC LENGTH:** Very short (less than half the diameter of the electrode)
- FLAT:** Angle electrode 10-15° from 90°
- VERTICAL-UP:** Use weaving technique
- VERTICAL DOWN:** Not recommended
- OVERHEAD:** Use slight whipping motion within the puddle
- STORAGE:** After opening, store in holding oven (250°F to 300°F) until used to ensure low hydrogen weld deposit
- RECONDITIONING:** If electrode has been exposed to the atmosphere for an extended period of time, place in 250°F oven and slowly increase temperature to 600°F; bake at 600°F for one (1) hour.

RECOMMENDED OPERATING PARAMETERS:

DIAMETER		TYPE OF POWER	MINIMUM AMPS	OPTIMUM* AMPS	MAXIMUM AMPS
INCHES	MM				
3/32	2.4	DCEP or AC	70	100	110
1/8	3.2	DCEP or AC	90	135	160
5/32	4.0	DCEP or AC	130	170	220
3/16	4.8	DCEP or AC	200	250	300
1/4	6.4	DCEP or AC	300	350	400

*For out of position welding, reduce amperages shown by 15%.

TYPICAL DEPOSITION DATA (AT OPTIMUM):

DIAMETER		TYPE OF POWER	AMPS	DEPOSITION RATE LBS/HR
INCHES	MM			
3/32	2.4	DCEP	100	2.00
1/8	3.2	DCEP	135	2.90
5/32	4.0	DCEP	170	3.80
3/16	4.8	DCEP	250	5.90
1/4	6.4	DCEP	350	8.20

AVAILABLE DIAMETERS AND PACKAGES:

DIAMETER		LENGTH		10-LB. CAN	50-LB. CAN
INCHES	MM	INCHES	MM		
3/32	2.4	14	355		S125332-Z35
1/8	3.2	14	355	S125344-Z33	S125344-Z35
5/32	4.0	14	355	S125351-Z33	S125351-Z35
3/16	4.8	14	355		S125358-Z35
1/4	6.4	18	457		S125381-Z35

Material Safety Data Sheets on any McKay product may be obtained from McKay Customer Service.

Because McKay is constantly improving products, McKay reserves the right to change design and/or specifications without notice.