



# 309 (H) Sterling® AP

AWS E309-16

Replaces 000131

160-C, INDEX: 020520

## DESCRIPTION:

The moisture resistant, all-position **309 (H) Sterling® AP** electrode is primarily designed for welding Type 309 metal but can also be used for 18-8 clad steels or dissimilar materials if the alloy content is sufficiently high for a sound, ductile deposit. It yields a uniform weld bead that is flat to slightly convex.

Note: Actual certs are included in every master carton of stainless stick electrodes at no charge.

Features	Benefits
<ul style="list-style-type: none"> <li>Spray-like arc transfer</li> <li>Easy strike and re-strike</li> <li>All-position</li> </ul>	<ul style="list-style-type: none"> <li>Low spatter, and less clean-up</li> <li>Easy to use, less chance of starting defects</li> <li>Welds extremely well in flat, horizontal, vertical (up) and overhead positions</li> </ul>
<ul style="list-style-type: none"> <li>Self-detaching slag</li> <li>Extremely high moisture resistance</li> <li>Directional arc</li> </ul>	<ul style="list-style-type: none"> <li>Less chance of slag inclusions</li> <li>Extends shelf life of product in open environments</li> <li>Metal goes where directed</li> </ul>

## TYPICAL WELD METAL PROPERTIES\* (CHEM PAD):

Weld Metal Analysis		AWS Spec
Carbon (C)	0.05	0.08 max
Chromium (Cr)	23.50	22.0 to 25.0
Nickel (Ni)	13.00	12.0 to 14.0
Molybdenum (Mo)	0.10	0.75 max
Manganese (Mn)	1.05	0.5 to 2.5
Silicon (Si)	0.56	0.90 max
Phosphorus (P)	0.020	0.04 max
Sulphur (S)	0.016	0.03 max
Copper (Cu)	0.10	0.75 max

## TYPICAL MECHANICAL PROPERTIES\* (AS WELDED):

		AWS Spec
Tensile Strength	88,000 psi (607 MPa)	80,000 psi
Yield Strength	67,000 psi (462 MPa)	not required
Elongation % in 2"	37%	30%
DeLong Ferrite Number Range	6-15	not required
Schaeffler Number Range	6-15	not required
WRC Number Range (1992)	6-15	not required

## CONFORMANCES AND APPROVALS:

- AWS Spec A5.4, Class E309-16
- ASME SFA5.4

\*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and McKay expressly disclaims any liability incurred from any reliance thereon. Typical data are obtained when welded and tested in accordance with AWS A5.4 specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by McKay.



# 309 (H) Sterling® AP

## RECOMMENDED WELDING PROCEDURES:

- GENERAL:** DCEP (electrode positive, work negative) or AC
- ARC LENGTH:** Short (less than half the diameter of the electrode)
- FLAT & HORIZONTAL:** Angle electrode 10-15° from 90°
- VERTICAL-UP:** Use weaving techniques or inverted V. Reduced amperage compared to flat position setting
- OVERHEAD:** Use slight weaving motion within the puddle
- STORAGE:** Sterling AP electrodes have a high degree of moisture resistance; however, for critical applications, the electrodes should be held at 225°F after opening.
- RECONDITIONING:** If exposed to atmosphere for extended periods, recondition at 500°F for 1 hour

## RECOMMENDED OPERATING PARAMETERS:

### ————— FLAT & HORIZONTAL —————

Diameter		Type of Power	Minimum Amps	Optimum Amps	Maximum Amps
Inches	mm				
3/32	2.4	DCEP or AC	45	65	80
1/8	3.2	DCEP or AC	55	105	120
5/32	4.0	DCEP or AC	65	140	170
3/16	4.8	DCEP or AC	160	170	205
1/4	6.4	DCEP or AC	180	200	225

## AVAILABLE DIAMETERS AND PACKAGES:

Diameter		Length		6-lb. Can	10-lb. Can
Inches	mm	Inches	mm		
3/32	2.4	10	254	S483830-032	—
1/8	3.2	14	355	—	S483844-033
5/32	4.0	14	355	—	S483851-033
3/16	4.8	14	355	—	S483858-033
1/4	6.4	14	355	—	S483880-033

Material Safety Data Sheets on any McKay product may be obtained from McKay Customer Service. Because McKay is constantly improving products, McKay reserves the right to change design and/or specifications without notice.

Sterling is a registered trademark of Hobart Brothers Company, Troy, Ohio.