

INCO-WELD® 347 is used for joining stabilized stainless steels such as 18/8/Nb or 18/8/Ti.

***Typical Chemical Analysis (%)**

Element	%	AWS Requirement
Carbon (C)	0.02	0.08 max
Chromium (Cr)	20.25	19.0-21.5
Nickel (Ni)	10.0	9.0-11.0
Molybdenum (Mo)	0.2	0.75
Manganese (Mn)	1.75	1.0 to 2.5
Silicon (Si)	0.48	0.30-0.65
Phosphorus (P)	0.002	0.03 max
Sulphur (S)	0.001	0.03 max
Copper (Cu)	0.1	0.75 max

***Typical Mechanical Properties**

Tensile Strength	90,000 psi
Yield Strength	59,000 psi
Elongation	42%
Charpy V-Notch (RT)	112 ft.lb
Charpy V-Notch (-320 deg F)	34 ft.lb

***Typical GMAW welding Parameters**

	Wire Diameter	Amperage	Voltage	Shielding
Short Circuit	.035"	80-160	14-22	90% He + 7½% Ar + 2½ O2
	.045"	110-220	15-23	90% He + 7½% Ar + 2½ O2
	.062"	130-250	16-23	90% He + 7½% Ar + 2½ O2
Spray Transfer	.035"	175-250	23-26	Ar + 2% O2
	.045"	225-325	24-29	Ar + 2% O2
	.062"	300-425	26-30	Ar + 2% O2

Approvals

AWS A5.9 ER347
ASME SFA 5.9
Canadian Welding Bureau

Available Sizes and Packaging

GTAW		GMAW		SAW	
Diameter	Packaging	Diameter	Packaging	Diameter	Packaging
1/16	10 lb. Tubes in 1 m Lengths	.030	30 lb. Spools/ Wire Baskets	3/32	60 lb. Coils
3/32		.035		1/8	
1/8		.045		5/32	
5/32		1/16			

*All information listed is provided as typical values and may differ from actual results due to variations in weld procedures. IAI disclaims any liability resulting from reliance on any of the above values.